

TRADEMARKPOLYETHYLENE

LLD2025 Series

Technical Data Sheet

LLDPE Injection / Masterbatch

Applications

- Closures
- Housewares
- Caps and Lids
- Masterbatch Color/ Additives

Properties

- Excellent Processability
- Ease of Blending
- Good Toughness
- Good Tear

Grades

- 2025 Pellets
- 2025G Granules

PROPERTIES

VALUE

METHOD

Melt Flow (gm/10min)	20.0	ASTM D1238
Density (gm/cc)	0.925	ASTM D1505
Tensile at Yield (psi)	1610	ASTM D638
Elongation at Break (%)	360	ASTM D638
1% Secant Modulus (psi)	37500	ASTM D790
Vicat Softening Temperature (°F)	203	ASTM D1525
Brittleness Temperature, F ₅₀ (°F)	< -105	ASTM D746
Hardness, Shore D	50	ASTM D2240

FDA

This material complies with FDA regulations in 21 CFR, section 177.1520.

Additional Information

All physical properties were tested using an injection molded sample.

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (expressed or implied, of merchantability, fitness or otherwise), or guarantee is made as to the suitability, accuracy, reliability, or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability, or completeness of such information for its particular use. There is no warranty against patent infringement, and Trademark Plastics Corporation shall not be liable for any loss, damage, or injury that may occur from use of this information. No statement herein shall be construed as an endorsement of any product or process.

For more information about our products, please contact your local sales representative or call 908.925.5900.