

TRADEMARKPOLYETHYLENE

LLH1918 Series

Technical Data Sheet

Applications

- Heavy Duty Sacks
- Liners
- Food Packaging
- Commercial Packaging

Properties

- Butene Comonomer
- Excellent Strength
- Excellent Drawdown
- Excellent Heat Seal

LLDPE Film Resin

Grades

- LLH1918B Barefoot
- LLH1918C No Slip & High Antiblock
- LLH1918F High Slip & Antiblock

PROPERTIES	VALUE	METHOD
Melt Index, MI ₂ (gm/10min)	1.0	ASTM D1238
Density (gm/cc)	0.918	ASTM D1505
Haze* (%)	19	ASTM D1003
Specular Gloss @ 45°	35	ASTM D2457
Dart Impact (gms/mil)	210	ASTM D1709
Elmendorf Tear MD/TD (g/mil)	350/625	ASTM D1922
Tensile at Break MD/TD (psi)	8100/6100	ASTM D882
Elongation at Break MD/TD (%)	580/690	ASTM D882
1% Secant Modulus MD/TD (psi)	29500/32000	ASTM D882

Typical film property as measured on a 1.0 mil blown film sample fabricated at a 2.5:1 B.U.R. *Base polymer only.

FDA

This material complies with FDA regulations in 21 CFR, section 177.1520, paragraph C, section 3.1(a).

Processing

Extrusion melt temperatures of 375° to 425°F are recommended for Trademark's LLH1918 Series with blowup ratios of 1.5:1 or higher.

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (expressed or implied, of merchantability, fitness or otherwise), or guarantee is made as to the suitability, accuracy, reliability, or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability, or completeness of such information for its particular use. There is no warranty against patent infringement, and Trademark Plastics Corporation shall not be liable for any loss, damage, or injury that may occur from use of this information. No statement herein shall be construed as an endorsement of any product or process.

For more information about our products, please contact your local sales representative or call 908.925.5900.